ENERSUN SSR1025-4 VENTED TUBULAR BATTERY

All Enersun SSR batteries utilise tubular positive plate construction, and are supplied in a powder coated steel tray. The tubular positive plate design helps to achieve maximum service life by reducing the shedding of the active material during service, while increasing the surface area of the plates. The tray provides additional protection and compression on the cells.

- Low self discharge characteristics
- High 'top-of-plate' electrolyte reservoir
- Designed for Australian Conditions


General Performance


pecifications	
Product No	15254
Battery	SSR1025-4
Nominal Capacity	1025Ah
Nominal Voltage	4VDC
Design Life (Years)	7 Years @ 20% DoD
Type of Application	Cyclic (Standby)

Efficiency at 10 hour rate (%)	
Ampere-Hour	>90%
Watt-Hour	>72%

Physical Properties

Plate Technology		
Tubular – Lead Antimony Alloy Spine (9.8mm)		
Flat Pasted – Lead Antimony Grid (4.1mm)		
1.260		
90mm		
3mm Steel Powder Coat		
Green		
Polypropylene (PP)		
Polypropylene (PP)		
103kg		
Lead Post M10 Bolt-on		
Microporous plastic		







Electrical Properties

Specifications	
Self discharge rate at 25°C	<5% per month
Short Circuit (Amperes)	4087A
Maximum Charge (Amperes)	88A
Normal charging (Amperes)	78A
Boost Voltage @ 25°C	2.50 Vdc per cell

Float voltage	
20°C	2.22 vpc
25°C	2.20 vpc
30°C	2.18 vpc

Actual Performance	
24 hour rate to 1.75vpc	867Ah
100 hour rate to 1.85vpc	1025Ah
120 hour rate to 1.85vpc	1050Ah

Number of cycles at 25°C	
20% DoD	3000
30% DoD	2700
50% DoD	2050
80% DoD	1400

For further information please contact Century Yuasa - Australia: 1300 364 877, New Zealand: 0800 236 8879

All reasonable care has been taken to ensure that the data presented in this document is accurate at the time of printing & for the purpose for which it is presented. Century Yuasa reserves the right to make changes to its products and information contained in this document without notice, and shall not be held liable for any loss or damage claimed to have arisen as a result of the use of this brochure.

